

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08K 5/14	A1	(11) International Publication Number: WO 93/25615 (43) International Publication Date: 23 December 1993 (23.12.93)
(21) International Application Number: PCT/US93/05127 (22) International Filing Date: 28 May 1993 (28.05.93) (30) Priority data: 07/896,265 10 June 1992 (10.06.92) US (71) Applicant: THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US). (72) Inventors: PRIDDY, Duane, B. ; 3207 Travis Court, Midland, MI 48642 (US). DEMIRÖRS, Mehmet ; Langs de Kreek 25, NL-4535 AA Terneuzen (NL). (74) Agent: DAMOCLES, Nemia, C.; The Dow Chemical Company, Patent Department, P.O. Box 1967, Midland, MI 48641-1967 (US).		(81) Designated States: AU, CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: OLIGOMERS OF STYRENE AS FLEGMATIZERS FOR ORGANIC PEROXIDES (57) Abstract A flegmatizer, which is an oligomer of styrene or of styrene and at least one comonomer, is admixed with an organic peroxide to reduce the heat- and/or shock-sensitivity of the peroxide. The resulting composition can be employed to polymerize olefinic monomers.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TC	Togo
DE	Germany	MD	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

OLIGOMERS OF STYRENE AS FLEGMATIZERS FOR ORGANIC PEROXIDES

The present invention relates to the use of shock- and/or heat-sensitive organic peroxides as initiators for the polymerization of olefinic compounds.

5 Many organic peroxides are known and used to initiate polymerization of monomers containing olefinic unsaturation. Many such peroxides are sensitive to shock and usually are handled only in diluted form. Generally, the addition of an appropriate diluent reduces the shock-sensitivity of the organic peroxide to the point where it can be safely handled. The problem of shock sensitivity of such peroxides has been recognized for many
10 years. See, e.g. U.S. Patent 4,178,263, which discloses diluting the peroxide with an olefinically unsaturated monomer which does not homopolymerize. According to said patent, monomers which exhibit no tendency to homopolymerize are those monomers which in admixture with an organic polymerization-inducing peroxide do not polymerize to more than one percent conversion of monomer to polymer at 100 hours at 40°C when the organic peroxide and
15 monomer are present in a one-to-one ratio by weight. Typical non-homopolymerizing monomers include: maleic anhydride, dimethyl maleate, diethyl maleate, citriconic anhydride, dimethyl citriconate, methyl citriconate, ethyl citriconate, fumaronitrile, methyl fumarate, dimethyl fumarate, ethyl fumarate, diethyl fumarate, cinnamionitrile, methyl cinnamate, ethyl cinnamate and stilbene. These monomers readily copolymerize with the basic monomer
20 present, e.g. styrene.

When diluted peroxide compositions are employed in the free-radical polymerization of olefinically unsaturated materials, the diluent material frequently has a deleterious effect on the resulting polymer; for example, in the polymerization of polystyrenes
25 materials such as oils, hydrocarbon diluents and high molecular weight hydrocarbons are not readily removed from the polymer after polymerization and result in a reduction in the heat-distortion temperature. When polymers made with organic peroxides are used in food contact applications, the diluent used with the peroxide must be nontoxic. In many countries, approval by a government agency is required for use of the diluent in the polymer. In the case of styrenic
30 polymers, the list of additives which meet the requirements for a good flegmatizer and which are also approved for food contact applications is very small. Examples of known flegmatizers include dioctyl phthalate, fatty acid esters, epoxidized soybean oil and mineral oil. Of these, only mineral oil and epoxidized soybean oil are approved over a wide geographic area for use in food contact applications. While mineral oil is approved for use in the preparation of
35 polystyrene for food contact applications, it is not a good flegmatizer for some new, highly polar initiators, as they are not soluble in the relatively nonpolar mineral oil.

In view of the deficiencies of the prior art solutions to the problem of flegmatizing organic peroxides for use in the polymerization of olefinically unsaturated monomers, it would be desirable to have a flegmatizer which is suitable for food contact applications, and which has polarity sufficient to be compatible with highly polar initiators.

5 Additionally, it would be desirable to have a flegmatizer which is an inert material, and which can easily be mixed with organic peroxide initiators to make them safe and easily handled.

The present invention includes such a flegmatizer, which is an oligomer of styrene or of styrene and at least one comonomer. Accordingly, the present invention includes a storage stable organic peroxide composition having reduced heat- and/or shock-sensitivity, the

10 composition comprising an organic peroxide and from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer comprising an oligomer of styrene, or of styrene and at least one comonomer.

In a second aspect, the invention is a method for reducing the heat- and/or shock-sensitivity of an organic peroxide, the method comprising admixing an organic peroxide with

15 from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer comprising an oligomer of styrene, or of styrene and at least one comonomer.

In another aspect, the invention is a method for polymerizing one or more olefinically unsaturated monomers, the method comprising admixing an organic peroxide with

20 from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer, and using the resulting mixture for the polymerization of an olefinically unsaturated polymerizable material, the flegmatizer comprising an oligomer of styrene or of styrene and at least one comonomer.

25 Advantageously, the flegmatizers of the present invention are compatible with a wide variety of organic peroxide initiators, are highly compatible with styrene-containing polymers and provide mixtures of organic peroxides which are safely and conveniently handled, and are suitable for use in food contact applications for styrenic polymers.

30 Polymers made using the flegmatizers of the present invention are useful in food packaging applications including, for example, packaging for yogurt, cookies, dairy products, fresh produce and meat.

In the present invention a flegmatizer is employed with an organic peroxide in

35 the polymerization of an olefinically unsaturated monomer.

The organic peroxides which can be employed in the present invention include shock- and/or heat-sensitive organic peroxides including, for example, propionyl peroxide, acetyl peroxide, succinic acid peroxide, t-butyl peroxyisobutylate, cyclohexanone peroxide, methyl ethyl ketone peroxide, 2,2-bis-(t-butyl peroxy)butane, 1,1-bis(t-butyl peroxy)cyclohexane, di-(t-butylperoxy)azelaate, t-butyl peroxy isopropyl carbonate, 2,5-dimethyl-2,5-bis(benzoylperoxy)hexane, t-butylperacetate, t-butylperbenzoate, and di-t-butylperoxy phthalate peroxide, benzoyl peroxide and 1,1-bis-t-butylperoxy-3,3,5-trimethylcyclohexane. Preferred organic peroxides are perketals, peresters and percarbonates. Mixtures of organic peroxides can be employed.

By the term "reduced shock-sensitivity" is meant a reduced E_{50} value as determined by Liquid Propellant Information Agency Test No. 4, Drop-Weight Test, Joint Army-Navy-Air Force Panel on Liquid Propellant Test Methods, Silver Springs, Md., USA, March 1960.

The flegmatizer of the present invention suitably is an oligomer of styrene or of styrene and at least one comonomer. Preferably, the oligomer has from 2 to 5 repeating units. More preferably, it has from 2 to 4 repeating units. Comonomers suitably present in the preparation of the flegmatizer include, for example, α -methylstyrene, acrylonitrile, methylmethacrylate, and p-methylstyrene. Styrene oligomers and styrene-acrylonitrile oligomers are preferred. Suitably, from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of the flegmatizer is employed. Preferably, from 25 to 75 percent of the flegmatizer is employed. Mixtures of flegmatizers can be employed.

The flegmatizers of the present invention can be readily prepared using methods well known to those skilled in the art. For example, polystyrene can be pyrolyzed/degraded at high temperature (300°C to 600°C). The volatile products formed are styrene oligomers and styrene monomers. After stripping the styrene monomer from the mixture of volatile products, a syrup remains which is suitable for use as a flegmatizer.

The flegmatized organic peroxy compositions of the present invention are readily prepared by admixing the flegmatizer and the peroxide using conventional techniques.

Organic peroxy initiator compositions in accordance with the present invention are useful for initiation of polymerization of a wide variety of monomers. Among the suitable ethylenically unsaturated monomers are, for example: styrene; styrene with alkyl and halogen substituents on the ring and side chain such as o-, m- and p-methyl styrenes, α -methylstyrene, 2,4-dimethyl styrene, 2,3-dimethyl styrene, 2,5-dimethyl styrene, alpha chlorostyrene, alpha ethyl styrene, p-ethylstyrene, m-propyl styrene, bromostyrene, dichlorostyrene, isopropenyl toluene, vinyl naphthalene, and the o-, m- and p-chlorostyrenes and bromostyrenes; esters of

alpha-methylene aliphatic monocarboxylic acids, such as methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, dodecyl acrylate, 2-chloroethyl acrylate, 2-chloropropyl acrylate, 2,2'-dichloroisopropyl acrylate, phenyl acrylate, cyclohexyl acrylate, methyl alpha-chloroacrylate, methyl methacrylate, ethyl methacrylate, methyl ethacrylate; acrylonitrile; methacrylonitrile; vinyl esters, such as vinyl acetate, vinyl chloroacetate, vinyl propionate, vinyl butyrate, vinyl laurate, vinyl stearate; vinyl ethers such as vinyl methyl ether, vinyl isobutyl ether, vinyl 2-chloroethyl ether; vinyl ketones, such as vinyl methyl ketone, vinyl hexyl ketone, methyl isopropenyl ketone; isobutylene; vinylidene halides, such as vinylidene chloride and vinylidene chlorofluoride; N-vinyl compounds such as N-vinyl pyrrole, N-vinyl carbazole, N-vinyl indole, N-vinyl succinimide; acrolein; methacrolein; acrylamide; methacrylamide; N-methylol acrylamide; and allyl compounds such as diallyl phthalate, tetrachlorodiallyl phthalate, allyl alcohol methallyl alcohol, allyl acetate, allyl methacrylate, diallyl carbonate, allyl lactate, allyl alpha-hydroxyisobutyrate, allyl trichlorosilane, allyl acrylate, diallyl malonate, diallyl oxalate, diallyl gluconate, diallyl methylgluconate, diallyl adipate, diallyl sebacate, diallyl citraconate, the diallyl ester of muconic acid, diallyl itaconate, diallyl chlorophthalate, diallyl dichlorosilane, the diallyl ester of endomethylene tetrahydrophthalic anhydride, triallyl tricarballylate, triallyl aconitate, triallyl citrate, triallyl cyanurate, triallyl phosphate, trimethallyl phosphate, tetraallyl silane, tetraallyl silicate and hexallyl disiloxane. Unsaturated olefins such as ethylene, propylene, butylene, hexene and exemplary monomers that can be employed with the initiators of this invention include, for example, 1,3-butadiene; isoprene; piperylene; 2,3-dimethyl-1,3-butadiene; 1,3-octadiene; 4,5-diethyl-1,3-octadiene; 3-methylstyrene; 3,5-diethylstyrene; 4-n-propylstyrene; 2,4,6-trimethylstyrene; 3-methyl-5-n-hexylstyrene; 2,3,4,5-tetramethylstyrene; 4-dodecylstyrene; 4-cyclohexylstyrene; 4-phenylstyrene; 4-p-tolylstyrene; 1-vinylnaphthalene; 2-vinylnaphthalene; 4-methyl-1-vinylnaphthalene; 3-ethyl-2-vinylnaphthalene; 4,5-dimethyl-1-vinylnaphthalene; 4,5-diethyl-2-vinylnaphthalene; 6-isopropyl-1-vinylnaphthalene; 2,4-diisopropyl-1-vinylnaphthalene and 4-n-propyl-5-n-butyl-2-vinylnaphthalene. The styrenic monomers are preferred, with styrene being most preferred. These monomers can be employed separately, or can be copolymerized according to methods well known to those skilled in the art.

Preferred polymers which can be made according to the present invention include, for example, polystyrene, styrene/acrylonitrile, styrene/acrylonitrile/N-phenylmaleimide, styrene/maleic anhydride, styrene/methyl methacrylate, styrene/butyl acrylate, styrene/acrylonitrile/butyl acrylate, HIPS, ABS, AES, and ABS/N-phenyl maleimide. Polymers made according to the present invention may include rubber. Polystyrene and polystyrene modified with rubber are more preferred polymers, with polystyrene being most preferred.

Polymerization of ethylenically unsaturated monomers employing the flegmatized organic peroxy compositions of the present invention may be conducted in any of the conventional polymerization systems such as bulk, mass, mass suspension, solution, suspension and emulsion polymerization. Mass polymerization is the preferred method. The flegmatized organic peroxy composition of the invention is employed in an amount sufficient to provide a conventional amount of peroxide initiator to the polymerization system. Suitably up to about 0.2 weight percent of peroxide initiator is employed based on the weight of the reaction mixture. Advantageously, from 50 ppm to 1,000 ppm of peroxide is employed. The flegmatized organic peroxy composition suitably is added to the monomer in the conventional manner. Advantageously, this addition is performed at ambient or lower temperatures.

The following Examples are given to illustrate the invention and should not be construed as limiting its scope. All parts and percentages are by weight unless otherwise indicated.

Example 1

One drop of t-butylperbenzoate is placed on a hot-plate at 400°C resulting in immediate detonation of the peroxide and leaving a dark brown residue. The peroxide is diluted to 25 percent active with styrene trimer and a drop of the mixture is placed on the hot-plate at 400°C. The mixture slowly decomposes without detonation or discoloration.

Example 2

A sample of t-butylperbenzoate is divided into two portions. One portion is flegmatized by dilution with an equal weight of a styrene-acrylonitrile (SAN) trimer which is obtained by condensing vapors which are produced by heating SAN copolymer.

A sample of styrene is divided into two portions. To one portion is added 500 ppm of t-butylperbenzoate without flegmatizer and to the other portion is added 500 ppm of SAN trimer flegmatized t-butylperbenzoate. Each of the styrene solutions is sealed in separate glass tubes (*in vacuo*). The sealed tubes are placed in an oil bath at 120°C for one hour. The tubes are opened and the syrups are analyzed for molecular weight and conversion to polystyrene. The styrene conversion and the polystyrene weight average molecular weight of both samples is 25 percent and 250,000, respectively. The presence of the flegmatizer has no significant negative effect upon the polymerization.

CLAIMS

1. An organic peroxide composition having reduced heat- and/or shock-sensitivity, the composition comprising an organic peroxide and from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer comprising an oligomer of styrene or of styrene and at least one comonomer.
- 5 2. The composition of Claim 1 wherein the amount of flegmatizer is from 25 to 75 weight percent.
3. The composition of Claim 1 wherein the peroxide is a perester, perketal or percarbonate.
- 10 4. The composition of Claim 1 wherein the peroxide is di(t-butylperoxy)azelate or t-butyl perbenzoate.
5. The composition of Claim 1 wherein the flegmatizer is an oligomer of SAN or styrene.
- 15 6. The composition of Claim 1 wherein the number of repeating units in the oligomer is from 2 to 5.
7. The composition of Claim 1 wherein the number of repeating units of the oligomer is from 2 to 4.
- 20 8. The composition of Claim 2 wherein the peroxide is a perester, perketal, or percarbonate, and the flegmatizer is an oligomer of SAN or styrene, wherein the number of repeating units is from 2 to 4.
- 25 9. A method for polymerizing one or more olefinically unsaturated monomers, the method comprising and mixing an organic peroxide with from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer, and using the resulting mixture for the polymerization of an olefinically unsaturated polymerizable material, the flegmatizer comprising an oligomer of styrene or of styrene and at least one comonomer.
- 30 10. A method for reducing the heat- and/or shock-sensitivity of an organic peroxide, the method comprising admixing an organic peroxide with from 10 to 90 percent, based on the total weight of the flegmatizer and the peroxide, of a flegmatizer comprising an oligomer of styrene or of styrene and at least one comonomer.

35

INTERNATIONAL SEARCH REPORT

PCT/US 93/05127

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C08K5/14		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C08K	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
A	US,A,4 178 263 (D.B. PRIDDY) 11 December 1979 cited in the application see column 1, line 60 - column 2, line 26; claim 1 ----	1-4
A	US,A,4 455 252 (K.B. WYLEGALA ET AL.) 19 June 1984 see column 2, line 37 - line 57 see claims 1,2,13,17; example 1 ----	1,3,4
A	EP,A,0 051 485 (CL INDUSTRIES) 12 May 1982 see claim 1; examples 6-8 -----	1
<p>¹⁰ Special categories of cited documents : 10</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p>		
IV. CERTIFICATION¹		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
08 SEPTEMBER 1993		17.09.93
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		ENGEL S.L.

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9305127
SA 75027

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08/09/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4178263	11-12-79	US-A- 4131728	26-12-78
US-A-4455252	19-06-84	None	
EP-A-0051485	12-05-82	US-A- 4396526	02-08-83

EPO FORM P007

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82